Dunedin Laboratory



200 Fryatt St, Dunedin Private Bag 1962, Dunedin 9054 **Telephone:** +64 3 477 6511 **Facsimile:** +64 3 477 7664

Report No: MAT:DUD20S-02695

www.fultonhogan.com 0800 LABORATORY

Material Test Report

Client: Jason Blair

Blackhead Quarries Ltd - 562521

Chadwick St

Fairfield, Dunedin

Project: QA-BHQ Sand: Dry Sand

PRELIMINARY REPORT ONLY

Date of Issue: 31/08/2020

Sample Details

Sample ID: DUD20S-02695
Client Sample ID: 3-5 sand
Material: 3 - 5 Sand
Sample Source: BHQ - Sand Dry
Site/Sampled From: SP @ Sand Plant
Date Sampled: 28/08/2020

Specification: No Specification (fine all sieves)

Sampled By: Jason Blair

Sampling Method: As Received - Not Accredited

Date Tested:31/08/2020Technician:Tim Wagner

Sampling Endorsed?: No

Other Test Results

Description Method Result Lim


Particle Size Distribution

Method: NZS 4407:2015 Test 3.8.2

Tested By: Tim Wagner

ı	Sieve Size	% Passing	Limits
	6.7mm	100	0 - 100
ı	14.75mm	100	0 - 100
	3.35mm	92	0 - 100
	2.36mm	22	0 - 100
	2.0mm 1.70mm	3	0 - 100
	1.70mm	1	0 - 100
	1.18mm	0	0 - 100

Chart



Comments

N/A