

Technical Data Sheet

Tested by Technical Department 28/08/2022	Checked by Technical Department 6/10/2022	Approved by Technical Manager 6/10/2022
---	---	---

Note: this data are measured values but not guaranteed values.
All testing methods according to JIS A 5905:2014

Run / Lot number **313B1**

Shipment							
Order Number (s)							
Shipmarks	Domestic market						
Additional Information							
Product	Customwood	MDF U MD AS/NZS E0				Pack Date	1/09/2022
Size(s)	4.75 x 2.44 x 1.22						

Property Data

		(Units)	Results
Thickness Nominal	公称厚さ	mm	4.75
Density	密度	g/cm ³	0.79
Moisture Content	含水率	%od	8.5
MOR (Bending Strength)	曲げ強さ	N/mm ²	>34
MOE (Modulus of Elasticity)	曲げヤング係数	N/mm ²	>3000
IB (Internal Bond)	はく離強さ	N/mm ²	1.11
Thickness Swell (24hr/20°C)	吸水厚さ膨潤率	%	<26
Screw Pull (JIS face)	木ねじ保持力	N	NA
Formaldehyde emission Average	ホルムアルデヒド放散量 平均	mg/L	0.2
Formaldehyde emission Maximum	ホルムアルデヒド放散量 最大	mg/L	0.3

[1]
[1]

Actual Thickness checks before crating:

Number of checks	サンプル数	8
Average Thickness	平均実測厚み	4.78 mm

[1] Formaldehyde emission by desiccator test based on the rolling average of product history.